

DIAMOND

ALKYD FINISH QD

C301

Product Description.

A high quality Quick dry alkyd topcoat. The product has good durability and offers good gloss and gloss retention. The product is available in many color shades and is easy to apply.

Designed For:

Recommended as top coat and touch up finishes


Marine: boot top, top sides, decks, engines and super structure

Protective: suitable for wide range of steel structure.

Technical characteristics

Shelf life:	36 months	Density	1.22 g/ml depend on shades
Flash point:	35°C	Colour:	colour shades
Volume solid:	49% by volume dependent on colour		
Texture:	semi matt	Theoretical spreading rate	16 m ² at 30µm

Application

	Mixing ratio	One component system. Stir the product well by using led or shaker. The Quantity depends on the method																		
	viscosity Potlife	20 to 30 second ISO 4 cup at 20C Four days in a sealed container																		
	Drying	<table><tr><td></td><td>10°C</td><td>25°C</td><td>35°C</td></tr><tr><td>Touch dry</td><td>5h</td><td>30 min</td><td>25 min</td></tr><tr><td>Dry to handle</td><td>17h</td><td>2 h</td><td>70 min</td></tr><tr><td>recoating</td><td>22h</td><td>12h</td><td>8h</td></tr></table>				10°C	25°C	35°C	Touch dry	5h	30 min	25 min	Dry to handle	17h	2 h	70 min	recoating	22h	12h	8h
	10°C	25°C	35°C																	
Touch dry	5h	30 min	25 min																	
Dry to handle	17h	2 h	70 min																	
recoating	22h	12h	8h																	
	Application	Airless: 180-150 Bar nozzle size0.48 -0.66 mm with thinner 5% Brush : Multicoat are required to achieve the specified dry film thickness. Volume of thinner: 0 - 10% Roller: not recommended Air spray 0-10% airless spray 0-5% brush 0 – 5% roller 0 – 5% Thinner: Use Rock thin 600																		
	No of coats	<table><tr><td></td><td>DFT</td><td>WFT</td><td>TSR</td></tr><tr><td>range</td><td>30 -50</td><td>60 -110</td><td>16 -10</td></tr><tr><td>recommended</td><td>30</td><td>80</td><td>16</td></tr></table>				DFT	WFT	TSR	range	30 -50	60 -110	16 -10	recommended	30	80	16				
	DFT	WFT	TSR																	
range	30 -50	60 -110	16 -10																	
recommended	30	80	16																	
storage		Store in cool dry place well ventilated and away from source of heat and ignition. Containers must be kept tightly closed.																		

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

DIAMOND

ALKYD FINISH QD

C301

Heat Fastness

Continuous: 120 °C Peak: up to 140 °C

pre-treatment

Surface preparation

Coated substrates All surfaces should be clean, dry and free from contamination. Surfaces should be treated in accordance with ISO 8504:2000. Ensure compatibility of the coated substrates with the selected paint system. If the remaining part of the existing coating system needs to be sweep-blasted, fine abrasive shall be used to avoid damage to the coating system. Contact your local Rock Coating office for more information.

Typical paint system

A typical system for this product is shown below and should be taken for guidance only. A full system specification where all details are taken into consideration can be obtained through your local Rock Coating representative.

Rock Prime 88

Recommended: 75µm DFT

Diamond QD

Recommended: 40µm DFT

Diamond QD

Recommended: 40µm DFT

For further information about full system specification consult your **ROCK COATING** supplier

Application conditions

The temperature of the substrate should be at least 3°C above the dew point of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is approx. 40°C. Higher steel temperatures are acceptable provided dry-spray is avoided by proper spray application and extra thinning if required. In extreme cases it may be necessary to reduce film thickness in order to avoid sag

Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators. As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spraying should be carried out under well-ventilated conditions. This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Disclaimer.

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.