

Rock Poxy Prime

Epoxy – based paint

C 221

Product description

Epoxy based primer contain anti corrosive zinc phosphate pigment with good adhesion properties for substrates (steel, aluminium, galvanised steel as per quality standard of protective coating industry

Designed For:

Suitable for structural steel and piping to be exposed to corrosive environments.
Recommended for offshore environments, refineries, power plants, bridges, buildings and mining equipment.

Technical characteristics

Shelf life: 36 months	Density: 1.6 ± 0.2 g/ml	Theoretical spreading rate: 5 m ² /l at 120µm
Colour: grey	Volume solid 60 ± 2 %	Texture: matt

Pre-treatment

Surface preparation

Blast cleaning The performance of this paint will depend on the degree of surface preparation. All surfaces should be clean, dry and free from contamination. Surfaces should be treated in accordance with ISO 8504:2000.

The surfaces shall be blast-cleaned to min. Sa 2, preferably Sa 2½ (ISO 8501-1:2007). The surface profile and the anchor pattern shall be between 40 µm and 70 µm. The abrasives shall be free from oil, grease, moisture, chloride contamination etc.

Power tool Cleaning

The performance of this paint will depend on the degree of surface preparation. Surfaces should be treated in accordance with ISO 8504:2000.

The surface shall be cleaned by high pressure steam/detergent cleaning to remove dirt, grease and/or salt deposits in accordance with SSPC SP1. Power-tool cleaning to min. St 2, preferably St 3 (ISO 8501-1:2007).

Care shall be taken to ensure that power-tool cleaning does not polish the steel surface. If the surface being prepared lies adjacent to a coated surface, the power tool cleaning shall overlap the coated surface by at least 25 mm and the coated surface shall be feathered

Coated substrates

All surfaces should be clean, dry and free from contamination. Surfaces should be treated in accordance with ISO 8504:2000. Ensure compatibility of the coated substrates with the selected paint system. If the remaining part of the existing coating system needs to be sweep-blasted, fine abrasive shall be used to avoid damage to the coating system. When recoating aged coated substrates, damaged areas must be removed back to a firm edge.

Light abrade or sweep-blast the surface in order to provide a physical key for adhesion. When recoating zinc primed products, ensure the primer has been fully cured.

Zinc salts products shall be removed by high pressure fresh water cleaning. Contact your local ROCK COATING office for more information

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules.
The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Rock Poxy Prime

C221

Application.

Application:

	Mixing ratio	Stir well before use. compound A 100 (vol.) Compound B 20 (vol.)																
	Sprayguns	Ideal application conditions for two-component EPOXY products: 20°C and a relative air humidity below 80%. Application not possible in temperatures below 10°C Airless gun: 180 - 250 Bar nozzle size 0.48 - 0.78mm thinner 5% Air spray: 4 -6 Bar nozzle size 1.5 - 2 mm thinner 10% Brush: multicoated are required to achieve the thickness Thinner 5% Roller: multicoated are required to achieve the thickness Thinner 5%																
	No of coats	<table><thead><tr><th></th><th>DFT</th><th>WFT</th><th>TSR</th></tr></thead><tbody><tr><td>Range</td><td>120-325</td><td>200-550</td><td>5-1.9m2</td></tr><tr><td>recommended</td><td>120</td><td>200</td><td>5</td></tr></tbody></table>		DFT	WFT	TSR	Range	120-325	200-550	5-1.9m2	recommended	120	200	5				
	DFT	WFT	TSR															
Range	120-325	200-550	5-1.9m2															
recommended	120	200	5															
	Drying time	<table><thead><tr><th>Surface temperature</th><th>Touch Dry</th><th>Dry to handle</th><th>Dry to recoat</th></tr></thead><tbody><tr><td>10°C</td><td>12 hours</td><td>24 hours</td><td>16 hours</td></tr><tr><td>25°C</td><td>5 hours</td><td>16 hours</td><td>7 hours</td></tr><tr><td>30°C</td><td>4 hours</td><td>12 hours</td><td>6 hours</td></tr></tbody></table>	Surface temperature	Touch Dry	Dry to handle	Dry to recoat	10°C	12 hours	24 hours	16 hours	25°C	5 hours	16 hours	7 hours	30°C	4 hours	12 hours	6 hours
Surface temperature	Touch Dry	Dry to handle	Dry to recoat															
10°C	12 hours	24 hours	16 hours															
25°C	5 hours	16 hours	7 hours															
30°C	4 hours	12 hours	6 hours															

TYPICAL PAINT SYSTEM

A typical system for this product is shown below and should be taken for guidance only

ROCK POXY prime 221	70 µm
ROCK MASTIC AL 222	120µm
ROCK THAN 333	50 µm

For further information about full system specification consult your **ROCK COATING** supplier

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Rock Poxy Prime

C221

APPLICATION CONDITIONS

The temperature of the substrate should be at least 3°C above the dew point. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is approx. 40°C. Higher steel temperatures are acceptable provided dry-spray is avoided by proper spray application and extra thinning if required. In extreme cases it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C, otherwise extra solvent may be required to obtain a proper application viscosity.

Storage and shelf life.

The product must be stored in accordance with national regulations. The cans are to be kept in a dry, cool, well ventilated space and away from source of heat and ignition. Cans must be kept tightly closed.

Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators. As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spraying should be carried out under well-ventilated conditions. This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Disclaimer.

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.
--

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.